



*Application
and
Maintenance
Guide*



www.TimberProCoatings.com

Log Ends Application

Log End Seal:

In the case of newly cut logs, Timber Pro recommends the use of Log End Seal to prevent rapid moisture loss, which results in checking and warping. The following application procedure is recommended:

- 1) Assure that there is no dirt built up on the log ends prior to application.
- 2) Apply the log end seal heavily by brush roller. Apply one or two coats as needed.
- 3) Allow proper drying of 16 hours between coats.

Note: Once the logs are ready to be finished with a coating, the log end seal needs to be ground off, as it will stop penetration of the final finish.





Timber Pro Coatings Canada

Unit 130-6251 Graybar Road
Richmond, BC, Canada V6W 1H3

Toll Free: 1-877-666-4244

Tel: (604) 270-4244

Email: canadainfo@timberprocoatings.com

06/2012

www.TimberProCoatings.com