



Roof Treatment

Technical Data Sheet

March 2013

Description

Timber Pro Roof Treatment is a premium exterior wood finish formulated with a unique blend of natural oils and resins. The Roof Treatment not only accentuates the natural beauty of the wood but it also provides unsurpassed protection against the damaging UV rays from the sun and destructive effects of the elements especially associated with roof shakes.

Where to Use

Timber Pro Roof Treatment can be used on all new and reconditioned wood roof shakes. Timber Pro Roof Treatment can be used on all wood species such as cedar and redwood. The following are areas of use for the Timber Pro Roof treatment.

- Roof shakes
- Roof Shingles

RESTRICTIONS

- Do not thin
- Do not apply over previously coated surfaces

Features and Benefits

- Can be used in interior and exterior wood surfaces
- Low V.O.C.
- Excellent UV protection
- Excellent weathering properties
- Large color range
- Easy soap and water cleanup

Roof Treatment

Technical Data Sheet

March 2013

Color Range and Packaging

Color:	(TR series) Transparent	24 colors available
	(ST series) Semi Transparent	18 colors available
	(SS series) Semi Solid	14 colors available

Packaging: 5 US Gallon Pail

Properties

Viscosity -	20-23 secs Zahn cup #2
Gloss Level -	Satin 25 - 35 GU @ 60 degree
Solids by Weight -	23.2% +/- 1%
Solids by Volume -	22.5% +/- 1%
V.O.C. -	94 g/l minus water
Weight per gallon-	8.42 lbs./Gal.
Specific Gravity-	1.01
Dry Time -	2-4 touch dry 16 hours through dry Note dry times will be extended at low temperatures and high humidity

Shelf Life

Approximately two years in an unopened container

KEEP FROM FREEZING

Coverage

Rough Wood: 100-150 square feet per gallon

Note: Coverage will vary with the porosity of the wood

Application

Use a spray applicator, nylon polyester brush

Clean Up

With soap and mild detergent

Product Disclaimer

The technical information and suggestions for use herein are based on Timber Pro Coatings Ltd research and experience and believed to be reliable. But such information and suggestions do not constitute a warranty. Since Timber Pro Coatings has no control over the conditions under which the product is transported, stored, handled, used or applied, buyers must determine for themselves by preliminary tests or otherwise the suitability of the product for their purposes.

Timber Pro Coatings Ltd

#130-6251 Graybar Rd, Richmond, BC V6W 1H3

Ph: 604-270-4244 Fax: 604-270-4247 Toll Free: 1-877-666-4244

Email: canadainfo@timberprocoatings.com